



Concordia Textiles nv
Flanders Fieldweg 37
8790 WAREGEM

Your notice of
31-01-2023

Your reference

Date
27-02-2023

Analysis Report 23.00563.01

Required tests :

EN 13561 4.14.2.3 Test 1 (2015)
ISO 1419-C (2019)

dimensional stability after artificial ageing
Determination of the ageing in climate

Sample id	Information given by the client	Date of receipt
T2302391	Tegels	31-01-2023



Elke Van De Walle
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.




Reference: T2302391 - Tegels

Dimensional stability after artificial ageing

Date of ending the test 27-02-2023
 Standard used EN 13561 4.14.2.3 Test 1 (2015)
 Product standard EN 13561 (2015)

Intern commentaar
 Deviation from the standard -
 Conditioning Min. 24 hours at 20°C and 65% rel. humidity
 Treatment 40°C and 100%RH
 Required number of hours 2h

	Length direction			Width direction		
	Dimension before (mm)	Dimension after (mm)	Shrinkage (%)	Dimension before (mm)	Dimension after (mm)	Shrinkage (%)
1#1	595	594	-0.2	595	595	+0.0
1#2	595	594	-0.2	595	595	+0.0
1#3	595	594	-0.2	595	595	+0.0
2#1	595	594	-0.2	595	595	+0.0
2#2	595	594	-0.2	595	595	+0.0
2#3	595	594	-0.2	595	595	+0.0
3#1	595	594	-0.2	595	595	+0.0
3#2	595	594	-0.2	595	595	+0.0
3#3	595	594	-0.2	595	595	+0.0
Average	595 mm	594 mm	-0.2 %	595 mm	595 mm	+0.0 %



Reference: T2302391 - Tegels

Determination of the ageing in climate

Date of ending the test	27-02-2023
Standard used	ISO 1419-C (2019)
Apparatus	CTS C-70/350
Temperature	40°C
Relative humidity	100%
Total duration (hours)	2

Sample generated: T2302391_01d